

FIBERFRAX PAPERS

Fiberfrax Papers are manufactured from Fiberfrax refractory ceramic fibres, blended with specially selected organic binders to give flexible papers with exceptional characteristics.

Advanced production techniques ensure a highly uniform structure enhanced by low thermal conductivity, good handling strength and a smooth surface. Fiberfrax Papers are available in a range of thicknesses and roll sizes.



General characteristics

Fiberfrax Papers have the following outstanding characteristics:

- High temperature stability
- High resiliency
- Lightweight
- Excellent flexibility
- Easy to wrap, cut and shape

Typical Applications

- High temperature gaskets and seals
- Ingot mould liners
- Automotive heat shields and silencer insulation
- Molten metal transfer systems (back-up insulation)
- Expansion Joints

Any new and/or special use of these products, whether or not in an application listed in our literature, must be submitted to our technical department for their prior written approval.

Handling Information

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

Typical Chemical Analysis (fibre wt. %)		
	FT	DS
SiO_2	50,0 – 54,0	50,0 – 54,0
Al_2O_3	46,0 – 50,0	46,0 – 50,0
Fe_2O_3	< 0,2	< 0,2
Alkalis	< 0,25	< 0,25

FIBERFRAX PAPERS

Typical Physical Properties		
	FT	DS
Colour	White	White
Melting Point (°C)	1800	1800
Product Density (kg/m ³)	200-240	160-200
Tensile Strength (kPa)	> 350	> 350
Paper Type	Unwashed	Washed
Classification Temp. (°C)*	1250	1250
Loss on ignition (wt. %)	< 12,0	< 12,0

Thermal Conductivity Data (W/mK)		
Mean Temp.	FT	DS
600°C	0.08	0.08
800°C	0.11	0.11
1000°C	0.17	0.17

Permanent Linear Shrinkage (%) 24 hour soak		
	FT	DS
1250°C	< 4.0	< 4.0
1400°C	-	-

*Classification Temperature is not a definition of the operational limit of these products, especially when long term physical or dimensional stability is a factor. For certain applications operational temperature limits may be significantly reduced. For assistance or clarification please contact us. Where appropriate Physical Properties data measured according to EN 1094-1.

Availability

Roll width (mm)	Thickness (mm)		Roll Length (m)		
	FT	DS	610	1000	1260
1	✓	✓	125	380	380
2	✓	✓	60	180	180
3	✓	✓	35	110	110
4	✓	✓	25	80	80
5	✓	✓	20	60	60
6	✓	✓	15	60	60
7	✓		15	50	50
8	✓		10	40	40

Fiberfrax papers are available with one sided aluminium foil.

Fiberfrax Papers

Fiberfrax FT Paper is a versatile insulating paper available in a wide range of thicknesses, and is suitable for use in a variety of high temperature applications.

Premium grade **Fiberfrax DS Paper** is produced using a unique washing process to give a paper designed for applications where extra cleanliness (less particulate) is required.

Insulcon B.V. - The Netherlands - Tel: +31 (0) 167 565750
Insulcon GmbH - Germany - Tel: +49 (0) 2131 408548-0
Insulcon N.V. - Belgium - Tel: +32 (0) 3 711 02 78
Insulcon Projects S.A. - Switzerland - Tel: +41 (0) 91911739-0

INSULCON
 LEADER IN HIGH TEMPERATURE SOLUTIONS
www.insulcon.com

Form: A1-127
 Effective: 03012022/ES
 Supersedes: 22052021/ED/fe
 All rights Reserved
 LD: UFeb13