### **WOVEN E-GLASS FIBRE TAPE – 550°C**

Woven tape is produced by weaving a number of yarns. The width and thickness are determined by the number and thickness of the yarns used.

Woven e-glass tape is a soft resilient product, available in a number of different thicknesses and constructions to provide a comprehensive HT range made from texturized, continuous E-Glass fibre filaments up to a maximum of 9 microns. These fibres cause considerably less irritation of the skin than coarser fibres.

Woven "ladder tapes" are also available. This type of webbing has regular perforations in the middle, to produce a ladder like structure.

#### **Chemical properties**

Woven e-glass tape exhibits excellent chemical stability resisting attack from most corrosive agents. Exceptions are hydrofluoric acids and phosphoric acids and concentrated alkalies. No water of hydration is present. Excellent die-electrical strength.

#### **Availability**

Woven e-glass tape is available in the following thicknesses: 2-5 mm, width 10-200 mm. Other sizes available on request. The webbing can be supplied with self adhesive backing, or with various special coatings. All E-Glass products are also available in a black version which is made by a colourfast lubricant.

## **Applications**

- Fire-resistant curtains
- Protective clothing
- Controlled cooling of castings
- Insulation of gas and steam turbines
- Welding curtains

- Insulation linings
- Wrapping of exhausts
- Flange jointing with opening for bolts ("ladder tapes")
- Radiant heat shields

# **Typical physical properties**

Average density : 600 – 800 kg/m<sup>3</sup>

Colour : White Basic composition : Silica

Continuous use limit : 550 °C Melting point : 840 °C

Insulcon B.V.- The Netherlands - Tel: +31 (0) 167 565750 Insulcon GmbH - Germany - Tel: +49 (0) 2131 408548-0 Insulcon N.V. - Belgium - Tel: +32 (0) 3 711 02 78

Insulcon Projects S.A. - Switzerland - Tel: +41 (0) 91911739-0



Form: A3-099 Effective: 10012022/ES Supersedes: 23022015/ND/an All Rights Reserved LD: 110012022

**TECHNICAL DATASHE**